#### FEATURES

- Controlled Particle Size
- High Chemical Purity
- High Brightness

#### BENEFITS

- Reduced Formula
  Viscosity
- Improved Processing
  Flowability
- Achieve Higher Loading Levels
- Improved Strength

#### SHIPPING INFORMATION

VICRON<sup>®</sup> FRP ships from Lucerne Valley, CA

Product is available in 50 lb. bags, supersacks, and bulk.

For availability and minimum order quantity, contact customer service.

#### SALES OFFICES

Lucerne Valley, CA 800-255-5832

Bethlehem, PA 800-801-1031

#### www.mineralstech.com

- ► GCC
- ► Talc
- Specialty PCC

© Specialty Minerals Inc. 7/2020

# VICRON<sup>®</sup> FRP

# Surface Treated, Finely Ground Calcium Carbonate


## **Product Description**

VICRON<sup>®</sup> FRP is a finely ground, high purity, coated calcium carbonate especially designed to improve flow and dispersion in polyester resin systems. The patented, proprietary surface treatment reduces viscosity and resin demand, allowing for higher loading levels and improved strength characteristics. This unique filler provides excellent flow in small mold cavities and tight channels in any composite application where fiber reinforcement is used. The consistent quality of VICRON FRP is assured by process controls in all areas of manufacturing from ore selection, milling practices and surface treating.

### **Typical Physical Properties**

Average Particle Size (microns)	6.5
Top Particle Size (microns)	30
Dry Brightness (Hunter Y, Rd Value)	97
Bulk Density (lbs./ft <sup>3</sup> )	36
Tap Density (lbs/ft <sup>3</sup> )	90
Surface Area (meters²/gram)	1.6
Specific Gravity	2.7
Chemical Composition (typical-before treatment)	
Calcium Carbonate (CaCO3)	98.5%
Magnesium Carbonate (MgCO3)	1.2%
Iron as (Fe <sub>2</sub> O <sub>3</sub> )	<0.03%
Moisture (H2O)	<0.2%

\*\*Values listed are typical, not to be considered as specifications of the product



All products are sold or otherwise provided on the understanding that the Buyer or other user is solely responsible for determining their suitability for the intended use. All information provided is based upon our research, is typical of the products, and is believed to be accurate, but no guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. SMI MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OR USE OF THE PRODUCTS DESCRIBED HEREIN. Inconsistent terms and conditions contained in Buyer's purchase order shall not be binding on SMI/BMI unless reflected in writing signed by SMI/BMI's representative. This information is not to be copied, used in evidence, released for publication or public distribution without written permission from Specialty Minerals Inc./Barretts Minerals Inc.

The Minerals Technologies Logo, Specialty Minerals Logo, and VICRON are registered trademarks of Minerals Technologies Inc. or its subsidiaries.

